

# WAKOL D 3045 Special primer

## Technical Information

### Area of application

Ready-to-use dispersion primer for facilitating adhesion of Wakol levelling compounds on

- WAKOL PU 280 Polyurethane Primer
- ceramic tiles
- natural stone flooring
- terrazzo
- cast asphalt

indoors.

### Special properties



1)



2)

- solvent-free according to TRGS 610
- non-slip surface
- suitable for underfloor heating
- ready-to-use

1) Based on the criteria of GEV (Association for Emission-controlled Laying Materials), classified as EMICODE EC1 PLUS: very low in emissions

2) Emission class according to French law

### Technical data

Raw material basis:	polyacrylate dispersion with aggregates
Drying time:	approx. 30 - 60 minutes
Cleaning agent:	fresh water
Storage time:	12 months at room temperature
Storage temperature:	not below +5°C; sensitive to frost
GISCODE:	D1
EMICODE according to GEV:	EC1 PLUS

Application and consumption<sup>3)</sup>:

Velour or foam roller      100 – 150 g/m<sup>2</sup>      WAKOL PU 280 Polyurethane Primer, tiles, natural stone flooring, terrazzo, cast asphalt

3) Consumption is dependent on surface structure and absorability of subfloor

## Subfloors

The subfloor and the climatic conditions of the room must meet the requirements of DIN 18356. Subfloors must be permanently dry, solid, level and free from cracks, dirt and adhesion-inhibiting substances. Use a suitable mechanical procedure to remove separating layers.

WAKOL D 3045 Special primer is intended for use on smooth, dense subfloors. On absorbent subfloors, use WAKOL D 3035 Disperion Primer, WAKOL D 3040 Primer Concentrate or WAKOL PU 280 Polyurethane Primer. Consult the respective codes for the areas of application and drying times.

## Usage

Stir primer before using. Apply WAKOL D 3045 Special Primer with velour or foam roller on the subfloor, avoiding puddle formation. Apply levelling compound after the primer has dried (suitable for walking); observe drying times.

## Important

Do not use at temperatures below +15°C. In cold weather, warm up WAKOL D 3045 Special primer in due time in heated room. All information is based on approx. 20°C and 65% relative air humidity.

We guarantee the uniform high quality of our products. All data is based on tests and many years of practical experience and refers to standardised conditions. The variety of materials used and the different construction site conditions, which lie beyond our control, preclude any claims based on this data. We therefore recommend making sufficient trials. Accompanying flooring manufacturer's instructions and the currently applicable codes must be observed. We gladly provide technical advice.

The product data sheets can be found in their latest version at [www.wakol.com](http://www.wakol.com).

This Technical Information of 04.03.2013 supersedes all previous versions.